



DECLASSIFIED

AECD - 2762

UNITED STATES ATOMIC ENERGY COMMISSION

THE CRYSTAL STRUCTURES OF CeB_4 , ThB_4 , AND UB_4

by

Allan Zalkin
D. H. Templeton

University of California
Radiation Laboratory

NAVY RESEARCH SECTION
SCIENCE DIVISION
REFERENCE DEPARTMENT
LIBRARY OF CONGRESS

MAR 14 1950

Date of Manuscript: November 22, 1949

Date Declassified: January 4, 1950

This document has been approved
for public release and sale; its
distribution is unlimited.

This document is reproduced as a project report and
is without editorial preparation. The manuscript has
been submitted to The Journal of Chemical Physics
for possible publication.

Issuance of this document does not constitute
authority for declassification of classified
copies of the same or similar content and title
and by the same authors.

Styled, retyped, and reproduced from copy
as submitted to this office.

Technical Information Division, ORE, Oak Ridge, Tennessee
AEC, Oak Ridge, Tenn., 3-2-50--900-A6585

Printed in U.S.A.

~~PRICE 5 CENTS~~

DECLASSIFIED

DTIC QUALITY INSPECTED 1

19950601 105

THE CRYSTAL STRUCTURES OF CeB₄, ThB₄, AND UB₄

By Allan Zalkin and D. H. Templeton

The compounds CeB₄, ThB₄, and UB₄ have been shown to crystallize in a new structure, which has been worked out from x-ray diffraction patterns. This structure is designated as the "ThB₄-type structure," since that was the compound first observed. These borides were prepared by D. L. Sawyer and L. Brewer of this laboratory, who heated the metals and boron together in vacuum at about 1500°C. Powder diffraction patterns were obtained of the three compounds. Rotation and Weissenberg patterns were obtained for [110] and [001] axes of a small single crystal of ThB₄. The patterns were indexed on tetragonal lattices whose dimensions are listed in Table 1.

Table 1—Lattice Parameters

	CeB ₄	ThB ₄	UB ₄
a	7.205 ± 0.008 Å	7.256 ± 0.004 Å	7.075 ± 0.004 Å
c	4.090 ± 0.005 Å	4.113 ± 0.002 Å	3.979 ± 0.002 Å
c/a	0.568	0.567	0.562
x-ray density	5.74 g/cm ³	8.45 g/cm ³	9.38 g/cm ³

Consideration of the intensities leads to the following structure for the metal atoms:

Space group D_{2h}⁵ - P4/mbm

4 Ce, Th, U in 4 (g): $\pm(\underline{u}, 1/2 + \underline{u}, 0; 1/2 - \underline{u}, \underline{u}, 0)$

$\underline{u} = 0.31$

These metal atoms are coplanar, with each having five nearly equidistant neighbors in the plane. Each metal atom has two neighbors in adjacent planes, but these are at a greater distance. This structure has holes, between the layers, which are best filled by boron atoms as follows:

4 BI in 4(e): $\pm(0, 0, \underline{v}; 1/2, 1/2, \underline{v})$

$\underline{v} = 0.2$

4 BII in 4(h): $\pm(\underline{w}, 1/2 + \underline{w}, 1/2; 1/2 - \underline{w}, \underline{w}, 1/2)$

$\underline{w} = 0.1$

8 BIII in 8(j): $\pm(\underline{x}, \underline{y}, 1/2; 1/2 + \underline{x}, 1/2 - \underline{y}, 1/2; \underline{y}, \underline{x}, 1/2; 1/2 + \underline{y}, 1/2 + \underline{x}, 1/2)$

$\underline{x} = 0.2$

$\underline{y} = 0.04$

Thus the compounds were assigned formulas of the type MB_4 , in agreement with the deduction, from the phases observed in various preparations, that the composition is between MB_2 and MB_6 .

This structure can be considered as a combination of two other more simple structures. Each atom BII is in a hole bounded by six metal atoms at corners of a triangular prism, as is the case with boron in the isostructural compounds AlB_2 ,¹ ZrB_2 ,² TiB_2 ,³ CrB_2 , NbB_2 , TaB_2 ,⁴ VB_2 ,⁵ and UB_2 .⁶ The atoms BI and BIII are grouped together as octahedra in holes bounded by metals at the corners of square prisms, analogous to the arrangement in the compounds CaB_6 , CeB_6 , ThB_6 , and others,⁷ in which a simple cubic array of metal atoms is interpenetrated by boron octahedra. The distances in the MB_4 compounds are in reasonable agreement with the corresponding ones in the MB_2 and MB_6 compounds.

A more detailed account of this work will be published subsequently.

REFERENCES

1. W. Hofmann and W. Jäniche, Z. phys. Chem., (B) 31: 214 (1936).
2. P. McKenna, Ind. Eng. Chem., 28: 767 (1936).
3. P. Ehrlich, Angew. Chem., 59: 163 (1947).
4. R. Kiessling, Acta Chem. Scand., 3: 90 (1949).
5. J. T. Norton, H. Blumenthal, and S. J. Sindeband, J. Metals, 1: 749 (1949).
6. A. Daane and N. C. Baenziger, USAEC Report ISC-53, July 1949, not yet published.
7. G. Allard, Bull. Soc. chim. France, 51: 1213 (1932); M. v. Stackelberg and F. Neumann, Z. phys. Chem., (B) 19: 314 (1932).

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

END OF DOCUMENT